

Globalprene 3566F

Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚合物

**Features 特性:**

- Linear block copolymer 線型嵌段共聚合物
- High strength and low viscosity 高強度及低黏度
- High tensile strength 高引張強度
- High rebound 高回復性

**Typical Application 一般應用:**

- Plastics modification 塑料改質
- Asphalt modification 瀝青改質
- Adhesives 黏著劑

Typical Properties	Test Method	Unit	Typical Value	Range
一般性質	測試方法	單位	數值	數值
Styrene content 苯乙烯含量	ASTM D5775	%	30	29~33
Specific Gravity 比重	ASTM D792	g/cc	0.93	N/A
Volatile Matter 揮發份	ASTM D5668	%	0.25	≤0.5
Ash Content 灰份	ASTM D5667	%	0.3	≤1.0
Melt Flow Index (190°C, 5kg) 熔融流動指數	ASTM D1238	g/10min	6	4~8
Hardness 硬度	ASTM D2240	Shore A	69	≥65

Packing 包裝： 50lb paper bag 50 磅紙袋

All ingredients in the product are in compliance with the following chemical inventories:

United States: Toxics Substances Control Act Inventory (TSCA)

Europe: European Inventory of Existing Chemical Substances (EINECS)

Canada: Canadian Domestic/ Non-Domestic Substances List (DSL)

Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

Australia: Australian Inventory of Chemical Substances

Korea: Korean Existing Chemicals List (KECL)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

EU Directive 2002/95/EC RoHS (Restriction of certain Hazardous Substances)

EC No 1907/2006 SVHC (Substances of Very High Concern)

CEN Standard EN71.3

Organo-tin Compounds

**Product Stewardship Information 產品責任資訊**

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

Head office 總公司 台北市八德路四段 83 號 3 樓  
3F, No.83, Sec. 4, Bade Road, Taipei 105, Taiwan

Tel : 886-2-2763-1611  
Fax : 886-2-27645749

USA office 美國 4903 Decker Drive Baytown, Texas 77520, USA

Tel : 1-281-424-6100  
Fax : 1-281-424-6169